RE8040-SN

Normal grade RO membrane element for sea water and high salinity well water

Permeate Flow rate :

Product Stabilized Salt 6,000 GPD (22.7 m³/day)

Specifications Rejection: 99.2 %

Effective Membrane 370 ft² (34.4 m²)

Area:

- The stated performance is initial data taken after 30 minutes of operation based on the following conditions; 32,000 mg/L NaCl solution at 800 psig (5.5 MPa) applied pressure, 8 % recovery, 77 °F (25 °C) and pH 6.5~7.0.
- 2. Minimum salt rejection is 99.0%.
- 3. Boron rejection is 88.0 % at pH 8.0 and 5 mg/L boron feed with the test condition as above note 1.
- 4. Permeate Flow rate for individual elements may vary but will be no more than 10 below the value shown.
- 5. Effective membrane area may vary within 5 %.
- All elements are vacuum sealed in a polyethylene bag containing 1.0 % SBS (Sodium bisulfite) solution and packaged individually in a cardboard box.

Product Membrane Type : Thin-film Composite

Description Membrane Material : PA (Polyamide)

Membrane Surface Charge: Negative


Element Configuration: Spiral-Wound, FRP wrapping

Product Dimensions

A= 40 inch (1,016 mm)

B= 8.0 inch (203 mm)

C = 1.12 inch (28 mm)



- 1. One interconnector (coupler) would be supplied for each membrane element.
- 2. SM membrane elements fit nominal 8.0-inch (203 mm) I.D. pressure vessel.
- 3. er feature may vary as design revisions take place.

Features

- * CSM SN element has good performance in terms of salt rejection and permeate flow rate, suitable for normal desalination process.
- * CSM SN element has a high chemical durability which prevents declining of its performance after CIP.

PRODUCT SPECIFICATION SHEET

Customer Satisfaction

Conditions for Handling CSM in general

Customers must keep the element boxes dry at room temperature to prevent them from freezing and damages from heat. If the polyethylene bag is broken, a new protective solution has to be added to the RO membrane element and the element has to be repackaged air-tight to prevent from biological growth. # Keep elements moist at all times after initial wetting # Permeate water obtained from first hour of operation should be discarded in order to flush the protective solution in the elements. # CSM elements should be immersed in a protective solution during storage, shipping or system shutdowns to prevent biological growth and freeze damage. The standard storage solution contains one (1) weight percent sodium bisulfite or sodium metabisulfite (food grade). For short term storage of one week, one (1) weight percent sodium metabisulfite solution is adequate for inhibiting biological growth. # The customer is fully responsible for the effects of incompatible chemicals on elements. Their use will void the element limited warranty.

Application Data

Operating Limits

	ent 15 psi				
(0.1 MPa) * Max. Pressure drop / 240" vessel					
60 psi (0.41 Mpa)					
■ Max. Operating pressure	1,200 psi (8.27				
	MPa)				
	66 gpm (15.0				
	m³/hr)				
 ⋇ Min. Concentrate flow rate	16 gpm (3.6 m ³ /hr)				
 ■ Max. Operating	113 °F (45 °C)				
temperature					
	3.0 ~ 10.0				
∝CIP nH range	2.0 ~ 11.0				

ж Max. Turbidity 1.0 NTU # Max. SDI (15 min) 5.0 # Chlorine concentration < 0.1 mg/L

Design Guideline for Various Water Source

esign Guideline for Various W	ater Source
*Waste water (SDI < 5) 8 ~ 12 gfd :	Waste wate
pretreated by UF (SDI < 3) 10 ~ 14	4 gfd
	7 ~ 10 gfd
5)	
# High salinity well water (SDI <	8 ~ 12 gfd
3)	
⊮ Surface water (SDI < 5)	12 ~ 16 gfd
surface water (SDI < 3) superior (SDI < 3)	13 ~ 17 gfd
	13 ~ 17 gfd
	21 ~ 30 gfd

Saturation Limits for Salts

⊭ CaSO₄	230 % 9	saturation	# SrSO₄	800 %
saturation a	⊭ BaSO₄	6,000 %	saturatio	n

SiO₂ 100 % saturation

Above values are saturation limit at the tail end of the membrane elements for each sparingly soluble salts with proper scale inhibitor.

CaCO₃ Scaling potential limits as LSI or SDSI

- # Without scale inhibitor < -0.2 # LSI (SDSI) with SHMP < +0.5 * LSI (SDSI) with special inhibitor¹ < +1.5 \approx SDSI with any inhibitor < +0.5
- 1. Special inhibitor means one of approved organic inhibitors. It should be approved from real plant for more than three